



FICHA TÉCNICA
TECHNICAL DATA SHEET
FICHE TECHNIQUE

DATA | DATE | DATE **25/05/2022**

PRODUTO VIDRADO REACTIVO VERDE
PRODUCT | PRODUIT VERT REACTIVE GLAZE | **ÉMAIL RÉACTIF VERT**
APRESENTAÇÃO PÓ
PRESENTATION | PRÉSENTATION POWDER | **EN POUDRE**
DESIGNAÇÃO VRG 308/4
DESIGNATION | DESIGNATION

DADOS RECOMENDADOS | RECOMMENDED DATA | DONNÉES RECOMMANDÉES

APLICAÇÃO GRÉS
APPLICATION STONEWARE | **GRÈS**

TEMPERATURA 1150 °C ± 20
TEMPERATURE | TEMPÉRATURE

COMPOSIÇÃO QUÍMICA

CHEMICAL COMP. COMP. CHIMIQUE

SiO₂ 41-51 %

Al₂O₃ 8-9 %

Fe₂O₃ <1 %

CaO 6-7 %

MgO <1%

ZnO 2-3 %

K₂O 1-2 %

Na₂O 1-2 %

PbO 8-9 %

ZrO₂ <1 %

Outros | Others | <25 %

Autres

CARACTERÍSTICAS FÍSICAS

PHYSICAL PROPERTIES | PROPRIÉTÉS PHYSIQUES

COEF. DE DILATAÇÃO TÉRMICA 20-400 °C
THERMAL EXPANSION COEF. | COEFFICIENT DILATATION THÉRIQUE

LINEAR | LINÉAIRE $\alpha 10^{-7}$ (1/K) 60,0±1,0

CÚBICO | CUBIC | CUBIQUE $\gamma 10^{-7}$ (1/K) 180±3,0

% RESIDUO 3,5±0,5
% RESIDUE | % RÉSIDU

OBSERVAÇÕES | OBSERVATIONS | OBSERVATIONS

OS VALORES PODEM VARIAR, DEPENDENDO DAS CONDIÇÕES DE UTILIZAÇÃO.

THE VALUES MAY VARY, DEPENDING ON THE CONDITIONS OF USE

LES VALEURS PEUVENT VARIER EN FONCTION DES CONDITIONS D'UTILISATION.

